

# JINAN EMI SHIELDING TECHNOLOGY CO.,LTD.

---

## THERMAL PAD TP1650



TEST ITEM	TEST MOTHOD	UNIT	VALUE
SIZE		mm	400*200MM
COLOR	Visual		PIINK
THICKNESS	ASTM D374	mm	0.25-10MM
GRAVITY	ASTM D792	g/cc	3.7±0.1
HARDNESS	ASTM D2240	Shore C	30±5
TENSILE STRENGTH	ASTM D412	Mpa	0.12
ELONGATION	ASTM D412	%	60
TEMP	EN344	°C	-40~+220
VOLUME RESISTIVITY	ASTM D257	Ω •CM	>10 <sup>11</sup>
VOLTAGE	ASTM D149	kv/mm	5
Weight Damnify	200°C 200H	%	≤1
Thermal Resistance	ASTM D5740	°C/ W	<0.1
FLAMMABLITY	UL-94		V-0
CONDUCTIVITY	ASTM D5470	w/(m•k)	16.5

---

Tel:0086-531-81901321 Fax:0086-531-81901393

E-mail:info@emishielding.com.cn

Website:www.emishielding.com.cn